

Key Benefits

- Genuine Kaneka MS polymer
- Optimal acoustic and moisture control
- Easy trowel formula
- High movement capacity
- No slumping or shrinkage
- Solvent and isocyanate free

Packaging 15kg Pail Pallet
48 Pails

Technical Data

Adhesive type	One Component MS Polymer	
Colour	Light Brown	
Maximum Tensile Strength	1.6 N/mm ²	ASTM D412
Shore Hardness A	40	ASTM C661
Elongation at Break	180%	ASTM D412
Low VOC Compliance	Yes	SCAQMD Rule #1168
VOC content	< 10g/L	USEPA Method 24
Shelf Life	12 months	
Application Temperature	+15°c - +40°c	
Service Temperature	-20°c - +90°c	
Tack Free Time	20-40 minutes	
Working Time (25°c & 50% RH)	30 minutes	